

Data Sheet* Advanced-PP 1102 LQ

Description

Advanced-PP 1102LQ is a propylene homopolymer with narrow MFR and general extrusion additivition. It is specifically designed for stretched tape yarn, carpet backing and artificial grass. Also suited for Raffia & Thermoforming Applications.

Application

Thermoformed Parts, Raffia, Carpet backing & General Extrusion.

Regulatory Information:

The Grade Advanced-PP 1102LQ and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments 1282/2011 & 1183/2012). Specific information is available upon request.

Properties (Typical values)

Properties	Unit	Test method	Value
Melt Flow Rate			
Melt flow rate (230°C / 2.16 KG)	g / 10 min	ISO 1133	4.5
Mechanical Properties			
Tensile modulus of elasticity (v= 1 mm/min)	MPa	ISO 527-2	1500
Tensile stress at yield (v= 50 mm/min)	MPa	ISO 527-2	34
Tensile strain at yield (v= 50 mm/min)	%	ISO 527-2	9
Tensile strain at break (v= 50 mm/min)	%	ISO 527-2	>50
Charpy impact strength unnotched (+23°C)	kJ/m ²	ISO 179/1eU	140
Charpy impact strength notched (+23°C)	kJ/m ²	ISO 179/1eA	3.5
Izod Impact strength Notched (+23°C)	kJ/m ²	ISO - 180 /1A	3.5
Ball indentation hardness (H 358/30)	MPa	ISO 2039-1	74
Thermal Properties			
Melting point, DSC	°C	ISO 3146	163
Heat deflection temperature ----- HDT/B (0.45 Mpa)	°C	ISO 75-2	85
Vicat softening temperature ----- VST/A50 (10 N)	°C	ISO 306	154
Other Properties			
Density	g / cm ³	ISO 1183	0.91

* Provisional

Values given here are typical and should not be interpreted as specification. In a view of many factors that may affects processing and application, these data do not relieve the receiver to this information from the responsibility of carry out their own test and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for specific purpose of the product made with or on the basis of the information in this publication.