

# Data Sheet Advanced-PP 1101 S

#### **Description**

Advanced-PP 1101 S is a polypropylene homopolymer fibre grade characterized by high flowability, medium molecular weight distribution. Advanced-PP 1101 S is particularly suitable for the production of continuous filaments (CF) and bulked continuous filaments (BCF) with phenol free anti gas fading stablization & inherent UV stability.

#### **Application**

CF/BCF

### **Regulatory Information:**

The Grade Advanced-PP 1101S and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments). Specific information is available upon request.

## **Properties (Typical values)**

| Properties                                    | Unit                | Test method | Value |
|---|---------------------|-------------|-------|
| Melt Flow Rate                                |                     |             |       |
| Melt flow rate (230°C / 2.16 KG)              | g / 10 min          | ISO 1133    | 24.0  |
| Mechnical Properties                          |                     |             |       |
| Tensile modulus of elasticity (v= 1 mm/min)   | MPa                 | ISO 527-2   | 1500  |
| Tensile stress at yield (v= 50 mm/min)        | MPa                 | ISO 527-2   | 35    |
| Tensile strain at yield (v= 50 mm/min)        | %                   | ISO 527-2   | 8     |
| Tensile strain at break (v= 50 mm/min)        | %                   | ISO 527-2   | >50   |
| Charpy impact strength unnotched (+23°C)      | kJ/m <sup>2</sup>   | ISO 179/1eU | 110   |
| Charpy impact strength notched (+23°C)        | kJ/m <sup>2</sup>   | ISO 179/1eA | 2.5   |
| Ball indentation hardness ( H 358/30)         | MPa                 | ISO 2039-1  | 78    |
| Thermal Properties                            |                     |             |       |
| Melting point, DSC                            | °C                  | ISO 3146    | 163   |
| Heat deflection temperatureHDT/B ( 0.45 Mpa)  | °C                  | ISO 75-2    | 85    |
| Vicat softening temperature<br>VST/A50 (10 N) | °C                  | ISO 306     | 154   |
| Other Properties                              |                     |             |       |
| Density                                       | g / cm <sup>3</sup> | ISO 1183    | 0.91  |

Values given here are typical and should not be interpreted as specification. In a view of many factors that may affects processing and application, these data do not relieve the receiver to this information from the responsibility of carry out their own test and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for specific purpose of the product made with or on the basis of the information in this publication.

Mar'17

Advanced Petrochemical Company Saudi Joint Stock Company الشركة المتقدمة للبتروكيماويات شركة مساهمة سعودية

Headquarters - Dammam P.O. Box 7215 Dammam 31462 Saudi Arabia Jubail P.O. Box 11022 Jubail 31961 Saudi Arabia Tel: +966 13 359 1000 Fax: +966 13 356 6065 C.R. 2055008094 Paid up capital: S.R. 1,967,940,000.00 المركز الرئيسي - الدمام ص.ب. ۷۲۱۰ - الدمام ۱۳۱۲ المملكة العربية السعودية الجبيل ص.ب. ۱۱٬۲۲ الجبيل ۱۳۱۹ المملكة العربية السعودية هاتف: ۱۱٬۱۳۳۰ ۱۳۳۹ + فاكس: ۲۰۲۱ ۱۳۳۵ ۱۲۲۲ س.ت. ۲٬۵۰٬۸٬۹۶ رأس المال المدفوع: ۱٬٬۹۲۷٬۹۶۰٬۱۰