

## Data Sheet\* Advanced-PP 1100R

### Description

Advanced-PP 1100R is a propylene homopolymer grade characterized by good flowability, good gloss, medium molecular weight distribution and medium crystallinity providing excellent and consistent process and product behaviour. Advanced-PP 1100R is particularly suitable for and Injection Molding applications requiring good organoleptic properties thus making it suitable for thin wall containers, caps & closures.

### Applications

Household articles, toys, thin wall molded containers for rigid packaging, caps & closures, compounding, etc.

### Regulatory Information:

The Grade Advanced-PP 1100R and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments). Specific information is available upon request.

### Properties ( Typical values)

Properties	Unit	Test method	Value
<b>Melt Flow Rate</b>			
Melt flow rate (230°C / 2.16 KG)	g / 10 min	ISO 1133	24.0
<b>Mechanical Properties</b>			
Tensile modulus of elasticity (v= 1 mm/min)	MPa	ISO 527-2	1500
Tensile yield at stress (v= 50 mm/min)	MPa	ISO 527-2	35
Tensile yield at strain (v= 50 mm/min)	%	ISO 527-2	8
Tensile strain at break (v= 50 mm/min)	%	ISO 527-2	>50
Charpy impact strength unnotched (+23°C)	kJ/m <sup>2</sup>	ISO 179/1eU	110
Charpy impact strength notched (+23°C)	kJ/m <sup>2</sup>	ISO 179/1eA	2.5
Ball indentation hardness ( H 358/30)	MPa	ISO 2039-1	78
<b>Thermal Properties</b>			
Melting point, DSC	°C	ISO 3146	163
Heat deflection temperature ----- HDT/ B ( 0.45 Mpa)	°C	ISO 75-2	85
Vicat softening temperature ----- VST/A50 (10 N)	°C	ISO 306	154
<b>Other Properties</b>			
Density	g / cm <sup>3</sup>	ISO 1183	0.91

\* Provisional

Values given here are typical and should not be interpreted as specification. In a view of many factors that may affect processing and application, these data do not relieve the receiver to this information from the responsibility of carry out their own test and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for specific purpose of the product made with or on the basis of the information in this publication.

Mar'14

Advanced Petrochemical Company  
Saudi Joint Stok Company

Headquarters - Dammam P.O. Box 7215 Dammam 31462 Saudi Arabia  
Tel: +966 3 809860 Fax: +966 3 8098750 C.R. 2050049604

Manufacturing Plant Site - Jubail P.O. Box 11022 Jubail 31961 Saudi Arabia  
Tel: +966 3 3591000 Fax: +966 3 356065 C.R. 2055008094  
Paid up capital: S.R. 1,639,950,000.00

www.advancedpetrochem.com

الشركة المتقدمة للبتروكيماويات  
شركة مساهمة سعودية

المركز الرئيسي - الدمام، ص.ب. ٧٢١٥ - الدمام ٣١٤٦٢ المملكة العربية السعودية  
هاتف: +٩٦٦٣٨٠٨٧١٠ فاكس: +٩٦٦٣٨٠٩٨٧٥٠ س.ت. ٢٠٥٠٠٤٩٦٠٤

إدارة المصنع - الجبيل، ص.ب. ١١٠٢٢ - الجبيل ٣١٩٦١ المملكة العربية السعودية  
هاتف: +٩٦٦٣٣٥٩١٠٠٠ فاكس: +٩٦٦٣٣٦٠١٠٦٠ س.ت. ٢٠٥٥٠٠٨٠٩٤  
رأس المال المدفوع: ١,٦٣٩,٩٥٠,٠٠٠.٠٠٠