

Data Sheet * Advanced-PP 1102M

Description

Advanced-PP 1102M is a polypropylene homopolymer for cast film applications. The grade does not contain any slip & anti-blocking agents.

Cast films, OPP films (double-bubble process), thermoforming, tape yarn, monofilaments, strapping.

Regulatory Information:
The Grade Advanced-PP 1102M and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments). Specific information is available upon

Properties (Typical values)

Properties	Unit	Test method	Value
Melt Flow Rate			
Melt flow rate (230°C / 2.16 KG)	g / 10 min	ISO 1133	8.0
Mechnical Properties			
Tensile modulus of elasticity (v= 1 mm/min)	MPa	ISO 527-2	1500
Tensile stress at yield (v= 50 mm/min)	MPa	ISO 527-2	35
Tensile strain at yield (v= 50 mm/min)	%	ISO 527-2	9
Tensile strain at break (v= 50 mm/min)	%	ISO 527-2	>50
Charpy impact strength notched (+23°C)	kJ/m²	ISO 179/1eA	3.5
Ball indentation hardness (H 358/30)	MPa	ISO 2039-1	77
Thermal Properties			
Melting point, DSC	°C	ISO 3146	163
Heat deflection temperature HDT/B (0.45 Mpa)	°C	ISO 75-2	85
Vicat softening temperatureVST/A50 (10 N)	°C	ISO 306	154
Other Properties			
Density	g/cm ³	ISO 1183	0.91

^{*} Provisional

Values given here are typical and should not be interpreted as specification. In a view of many factors that may affects processing and application, these data do not relieve the receiver to this information from the responsibility of carry out their own test and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for specific purpose of the product made with or on the basis of the information in this publication.

Advanced Petrochemical Company Saudi Joint Stock Company

Headquarters - Dammam P.O. Box 7215 Dammam 31462 Saudi Arabia Jubail P.O. Box 11022 Jubail 31961 Saudi Arabia Tel: +966 13 359 1000 Fax: +966 13 356 6065 C.R. 2055008094 Paid up capital: S.R. 1,967,940,000.00

الشركة المتقدمة للبتروكيماويات شركة مساهمة سعودية

المركز الرئيسي - الدمام ص.ب. ٧٢١٥ - الدمام ٣١٤٦٢ المملكة العربية السعودية الجبيل ص.ب. - ١١.٢٢- الجبيل ١٩٩٦ المملكة العربية السعودية هاتف: ...ا ۱۳۵۹ ۱۳۳۰ فاکس: ۲.۵ ۲۵۳ ۱۳۳۰ س.ت. ۸.۹۶۴ رأس المال المدفوع: ١,٩٦٧,٩٤.,...